

**lonac® NM-91** is a highly regenerated mixed bed ion exchange resin consisting of a 55 % cation component and a 45 % anion component. **lonac® NM-91** is characterized by high cation exchange capacity. **lonac® NM-91** is specifically designed for water with high Alkalinity to FMA ratios, where complete removal of silica and CO  $_2$  is not required.

The resin mixture is ready for use without regeneration. Ionac® NM-91 is especially suitable:

» in mixed bed units for central polishing after primary demineralization plants

It also can be used for demineralization of service water in small and very small units for:

- » EDM recycling
- » laboratories and photo laboratories
- » household appliances (e.g. steam irons, air humidifier)
- » small industrial plants (e.g. refilling of starter batteries or coolant circuits)
- » water for watering

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Ion Exchange Resins.





### **General Description**

Ionic form as shipped	H+/OH-
Functional group	sulfonic acid/quart. amine type I
Matrix	crosslinked polystyrene
Structure	gel type beads
Appearance	dark brown - black, translucent

### Physical and Chemical Properties

		metric units			
Operating capacity*	breakthrough point 1 megohm*cm	min. eq/l	0.30		
Fines*	< 0.315 mm	max. vol. %	2		
Coarse beads*	> 1.25 mm	max. vol. %	5		
Bulk density	(+/- 5 %)	g/I	740		
Density		approx. g/ml	•	1.2	
Water retention		wt. %	50	-	60
Volume change	H+/OH>Ca, Mg/Cl, SO <sub>4</sub>	max. vol. %	- 20		
Stability	at pH-range		0	-	14
Storability	of the product	max. years		2	
Storability	temperature range	°C	-20	-	40

<sup>\*</sup> Specification values subjected to continuous monitoring.





### Recommended Operating Conditions\*

		metric units		
Operating temperature		max. °C	60	
Operating pH-range			0 - 14	
Bed depth		min. mm	600	
Specific pressure drop	(15 °C)	approx. kPa*h/m²	1.5	
Pressure drop		max. kPa	200	
Linear velocity	operation	max. m/h	60	

<sup>\*</sup> The recommended operating conditions refer to the use of the product under normal operating conditions. It is based on tests in pilot plants and data obtained from industrial applications. However, additional data are needed to calculate the resin volumes required for ion exchange units. These data are to be found in our Technical Information Sheets.

Edition: 2010-08-27

Previous Edition: 2009-11-18





### Additional Information & Regulations

#### Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

#### **Toxicity**

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

#### **Disposal**

In the European Community Ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

#### **Storage**

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

lewatit@lanxess.com

D-51369 Leverkusen

**BU ION** 

Lanxess Deutschland GmbH

www.lewatit.com www.lanxess.com

This document contains important information and must be read in its entirety.

Edition: 2010-08-27

Previous Edition: 2009-11-18

